



US009409472B2

(12) **United States Patent**
Hatanaka et al.

(10) **Patent No.:** **US 9,409,472 B2**
(45) **Date of Patent:** **Aug. 9, 2016**

(54) **ENGINE MOUNT**

F16F 1/376; F16F 1/377; B60K 5/1208;
B60K 5/1233

(71) Applicant: **TOYOTA JIDOSHA KABUSHIKI**
KAISHA, Toyota-shi, Aichi-ken (JP)

See application file for complete search history.

(72) Inventors: **Keishi Hatanaka**, Yatomi (JP); **Noriaki Yoshii**, Nagoya (JP); **Yasuo Suzuki**, Komaki (JP); **Hitoshi Yamaguchi**, Toyokawa (JP); **Shinji Komura**, Toyota (JP)

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,079,168	A *	3/1978	Schwemmer	B29C 63/48
					156/283
6,292,995	B1 *	9/2001	Corbin	C08J 5/124
					156/307.3
8,709,195	B2 *	4/2014	Halladay	C09J 121/00
					156/283
2006/0214341	A1 *	9/2006	Sugiura	F16F 1/3842
					267/293

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

FOREIGN PATENT DOCUMENTS

JP	H10-281225	A	10/1998
JP	2009-036295	A	2/2009

* cited by examiner

Primary Examiner — Thomas J Williams

(74) *Attorney, Agent, or Firm* — Oliff PLC

(21) Appl. No.: **14/718,822**

(22) Filed: **May 21, 2015**

(65) **Prior Publication Data**

US 2015/0352939 A1 Dec. 10, 2015

(30) **Foreign Application Priority Data**

Jun. 5, 2014 (JP) 2014-117098

(51) **Int. Cl.**

F16F 1/38 (2006.01)

B60K 5/12 (2006.01)

F16F 1/373 (2006.01)

(52) **U.S. Cl.**

CPC **B60K 5/1208** (2013.01); **F16F 1/373** (2013.01); **F16F 1/3849** (2013.01); **F16F 1/3856** (2013.01); **F16F 2226/02** (2013.01)

(58) **Field of Classification Search**

CPC F16F 1/36; F16F 1/38; F16F 1/3842; F16F 1/3856; F16F 1/3849; F16F 1/373;

(57) **ABSTRACT**

Provided is an engine mount for a power unit. The power unit is supported by a support via the engine mount. The engine mount includes a first mounting bracket, a second mounting bracket, and a coating film. The coating film is applied to at least one of a surface of a first mounting portion and a surface of a second mounting portion. The coating film includes a cured-resin base layer made of a phenolic-resin adhesive, and an outer layer made of an epoxy-resin antirust paint and laminated on the cured-resin base layer. A thickness of the cured-resin base layer is 5 μm or more. A thickness of the outer layer is less than 15 μm . A sum total of the thickness of the cured-resin base layer and the thickness of the outer layer is equal to or more than 15 μm and equal to or less than 30 μm .

5 Claims, 3 Drawing Sheets

